

PRODUCT INFORMATION

Category	Speciality Filled & Reinforced Polypropylene Compound
Grade Name	HR 8215 PO UV
Features	20% Mineral Filled Polypropylene Black Compound With 2000 hours UV Stability, Very Good Mechanical Properties and Heat Aging Stability
Application	Automotive and Appliances
Component	Extrusion & Blow Moulding , duct assembly

Typical Properties	ASTM Method	Units	Typical Value
Melt Flow Index	D 1238	Gms/10min	0.6 – 1.0
Specific Gravity	D 792	—	1.05 ± 0.02